

Appl. No. 10/006,231
Amendment dated: December 30, 2003
Reply to OA of: October 24, 2003

This listing of claims will replace all prior versions and listings of claims in the application.

Listing of Claims:

Claims 1-13(canceled).

14(currently amended). A wax decoration item comprising a mixture of polyethylene wax, cyanide polymer and paraffin white wax; wherein the weight ratio between the polyethylene wax, the cyanide polymer and the white wax is 3-6% : 7-11% : 85-88%, the melting temperature and the condensing temperature located in a range of 80-170 degrees Celsius.

Claim 15(canceled).

16(original). The wax decoration item as claimed in claim 14, wherein the preferred weight ratio between the polyethylene wax, the cyanide polymer and the white wax is 4.5% : 9% : 86.5%, the melting temperature and the condensing temperature being 125 degrees Celsius.

17(currently amended). The wax decoration item as claimed in claim 14, wherein a colloid material is coated ~~to the wax decoration item~~ onto the outer peripheral surface of the wax decoration item and the melting temperature and the condensing temperature of the colloid material are lower than those of the wax decoration item.

18(previously presented). The wax decoration item as claimed in claim 17, wherein the colloid material is a mixture of the cyanide polymer and the white wax, the weight ratio between the cyanide polymer and the white wax is 7-11% : 89-93%, the

Appl. No. 10/006,231
Amendment dated: December 30, 2003
Reply to OA of: October 24, 2003

melting temperature and the condensing temperature located in a range of 75-140 degrees Celsius.

19(original). The wax decoration item as claimed in claim 17, wherein the colloid material in step 4 is a mixture of the cyanide polymer and the white wax, the preferred weight ratio between the cyanide polymer and the white wax is 9% : 91%, the melting temperature and the condensing temperature being 120 degrees Celsius.

Claim 20(original). The wax decoration item as claimed in claim 14, further comprising inorganic pigment added in the mixture of the polyethylene wax, the cyanide polyethylene wax, the cyanide polymer and the white wax.

21(original). The wax decoration item as claimed in claim 14, further comprising inorganic pigment added in the colloid material.

22(original). The wax decoration item as claimed in claim 14, further comprising fragrance added in the mixture of the polyethylene wax, the cyanide polymer and the white wax.

23(original). The wax decoration item as claimed in claim 14, further comprising fragrance added in the colloid material.

24(original). The wax decoration item as claimed in claim 14, further comprising a wick in the mixture of the polyethylene wax, the cyanide polymer and the white wax, the wick extending out from the colloid material.